


WHAT IS CLAIMED IS:

1. An aliphatic polyester resin composition contains a compound (A) of 1.0 mass part to 100 mass parts expressed by the following formula (1) as a plasticizer to an aliphatic polyester of 100 mass parts.

Formula (1)



- In the formula, X denotes a trivalent polyalcohol frame;  $R^1$ ,  $R^2$ ,  $R^3$  are selected from an acyl group having 2 to 18 carbon atoms or a hydrogen atom; the sum total of carbon numbers of  $R^1$ ,  $R^2$ ,  $R^3$  is 10 to 22; and the average acylation rate is 50 to 90%.

2. The aliphatic polyester resin composition according to the claim 1, wherein  $R^1$ ,  $R^2$ ,  $R^3$  of the formula (1) contain at least one acyl group having a carbon number of 8 to 18.

3. The aliphatic polyester resin composition according to the claim 1 or 2, wherein the aliphatic polyester resin is a lactic acid system polyester.

4. Sheets, films, or other products molded from the aliphatic polyester resin composition described in any one of the claims 1 to 3.